

AFRICAN PADOUK QUARTER CUT VENEER

Latin names: Pterocarpus soyauxi Taub., P. tinctorius Welw.

Commercial Names: (I) Padouk africano (F) Padouk, (D) Afrikanisches padouk, (E) Padouk

Original names: Padouk, Osun, Muenge, Corail, Palo rosa, M'be, Barwood

Mechanical properties: Average resistance to longitudinal compression: 65N/mm^2
Bending strength: 140N/mm^2
Modulus of elasticity: 11.000 N/mm^2
Density: 760kg/m^3 12% MC
Dimensional changes: small to medium
Hardness: medium
Texture: to fine
Porosity: quite high.

