

## ASH BURL VENEER

**Latin names:** Fraxinus excelsior L. and Fraxinus ornus L.

**Commercial Names:** (I) Frassino, (F) Frene, (D) Esche, (E) Fresno

**Original names:** Frassino, Frene, Esche

**Mechanical properties:** Average resistance to longitudinal compression:  $50\text{N/mm}^2$

Bending strength:  $105\text{N/mm}^2$

Modulus of elasticity:  $12.500\text{ N/mm}^2$

Density:  $720\text{kg/m}^3$  12%MC

Dimensional changes: medium

Hardness: good

Texture: medium

Porosity: quite high.



# DANUBE

No.1 building material company