

## ASH VENEER

**Latin names:** Fraxinus excelsior L. and Fraxinus ornus L.

**Commercial Names:** (I) Frassino, (F) Frene, (D) Esche, (E) Fresno

**Original names:** Frassino, Frene, Esche

**Mechanical properties:** average resistance to longitudinal compression: 50N/mm<sup>2</sup>

Bending strength: 105N/mm<sup>2</sup>

Modulus of elasticity: 12.500N/mm<sup>2</sup>

Density: 720kg/m<sup>3</sup> 12% MC

Dimensional changes: medium

Hardness: good

Texture: medium

Porosity: quite high.



# DANUBE

No.1 building material company