

BIRCH VENEER

Latin names: Betula alba

Commercial Names: (I)Betulla bianca, Betulla finlandese, (F) Buoleau blanc
(D) Birche, Weissbirche, (E) Abedul

Original names: Betulla bianca , Birche , Abedul

Mechanical properties: Average resistance to longitudinal compression: 46N/mm^2

Bending strength: 85N/mm^2

Modulus of elasticity: 13.000N/mm^2

Density: 600kg/m^3 12%MC

Dimensional changes: medium

Hardness: medium to good

Texture: fine

Porosity: low



DANUBE

No.1 building material company