

BUBINGA VENEER

Latin names: Guibourita demeusei

Commercial Names: Bubinga name of veneer: Kevazingo

Original names: Cameroon: Bubinga, Essingang, Ovang Guinea

Mechanical properties: Average resistance to longitudinal compression: 57N/mm^2

Bending strength: 122N/mm^2

Modulus of elasticity: 11.000 N/mm^2

Density: 850kg/m^3 12% MC

Dimensional changes: medium

Hardness: medium

Texture: medium

Porosity: quite high.



DANUBE

No.1 building material company