

CHERRY VENEER

Latin names: Prunus serotina

Commercial Names: (I)Ciliegio, (F) Ceriser, (D) Kirschbaum, (E) Cerezo

Original names: Ciliegio , ceriser , Kirschbaum

Mechanical properties: Average resistance to longitudinal compression: 42N/mm²

Bending strength: 80N/mm²

Modulus of elasticity: 7.700N/mm²

Density: 850kg/m³ 12%MC

Dimensional changes: medium to large

Hardness: medium

Texture: medium

Porosity: medium



DANUBE

No.1 building material company