

CAROLINA BIRCH BURL VENEER

Latin names: Betula alba.

Commercial Names: (I) Betulla bianca, Betulla finlandese , (F) Bouleau blanc, (D) Birche Weissbiche , (E) Abedul

Original names: Betulla bianca , Birche , Abedul

Mechanical properties: Average resistance to longitudinal compression: 46N/mm²

Bending strength: 85N/mm²

Modulus of elasticity: 13.00N/ mm²

Density: 600kg/m³ 12%MC

Dimensional changes: medium

Hardness: medium

Texture: fine

Porosity: low.



DANUBE

No.1 building material company