

DYED WENGE VENEER

Latin names: Millettia laurenti De Wild. , M. stuhlmanni Taub.

Commercial Names: (I) Wenge-

Original names: Awong , Anong, Mokonge , Kiboto

Mechanical properties: average resistance to longitudinal compression: 65N/mm^2

Bending strength: 150N/mm^2

Modulus of elasticity: 11.500N/mm^2

Density: 780kg/m^3 12%MC

Dimensional changes: medium

Hardness: fairly low

Texture: medium to coarse

Porosity: quite high.



DANUBE

No.1 building material company