

## EBONY VENEER

**Latin names:** Diospyris celebica.

**Commercial Names:** (I) Ebana Macassar, (F) Ebene de Macassar, (D) Macassar Ebenholz, (E) Haya

**Original names:** Kayu Hitam

**Mechanical properties:** Average resistance to longitudinal compression:  $68\text{N/mm}^2$

Bending strength:  $138\text{N/mm}^2$

Modulus of elasticity:  $14.000\text{ N/mm}^2$

Density:  $1.100\text{kg/m}^3$  12%MC

Dimensional changes: medium

Hardness: very good

Texture: medium

Porosity: medium.

