

ELM BURL VENEER

Latin names: Ulmus montano stokes amd Ulmus campestris Auct.

Commercial Names: (I) Olmo, (F) Orme , (D) Ulme, (E) Olmo

Original names: Ulme, Ormo, Ormadel, Oll

Mechanical properties: Average resistance to longitudinal compression: 55N/mm^2

Bending strength: 100N/mm^2

Modulus of elasticity: 10.300N/mm^2

Density: 620kg/m^3 12%MC

Dimensional changes: medium

Hardness: medium

Texture: medium

Porosity: quite high.

