

FIGURED SYCAMOREVENEER

Latin names: Various species belong to botanical genus acer among these the Following important in Italy. Acer campestre L., A. pseudoplatanus L., A. opalus mill and A. platanoides.

Commercial Names: (I)Acero (F) Erable,(D) Ahorn,(E) Arce , Sicomoro , (USA) European Maple

Original names: Oppio , Rompich , Aierela , Testuccio

Mechanical properties: Average resistance to longitudinal compression: 45N/mm²

Bending strength: 110N/mm²

Modulus of elasticity: 9.400N/mm²

Density: 660kg/m³ 12%MC

Dimensional changes: medium

Hardness: good

Texture: fine

Porosity: low



DANUBE

No.1 building material company