

KOTO VENEER

Latin Name: Pterygota macrocarpa K. Schum , Wild

Commercial Names: (I) Koto , (Tay) , (F) Koto

Original Names: Koto , Bontue , Pohouro , Kunbi

Mechanical Names: Average resistance to longitudinal compression: 55N/mm^2
Bending Strength: 120N/mm^2
Modulus Of Elasticity: 11.500N/mm^2
Density: 600kg/m^3 12%MC
Dimensional Changes: Medium
Hardness: Fairly low
Texture: medium to coarse
Porosity: Quite high.



DANUBE

No.1 building material company