

LACE WOOD RED VENEER

Latin names: Drimys winteri

Commercial Names: (I) Lace

Original names: Casca d'Anta , Catara , Chachaca

Mechanical properties: Average resistance to longitudinal compression: 48N/mm^2

Bending strength: 87N/mm^2

Modulus of elasticity: 13N/mm^2

Density: 550kg/m^3 12%MC

Dimensional changes: medium

Hardness: medium

Texture: medium

Porosity: medium



DANUBE

No.1 building material company