

MAKORE VENEER

Latin names: Prunus avium

Commercial Names: (I) Ciliegio (F) Cerisier, (D) Kirschbaum, (E) Cerezo

Original names: Ciliegio, Cerisier, Kirschbaum, Cerezo

Mechanical properties: Average resistance to longitudinal compression: 42N/mm^2

Bending strength: 80N/mm^2

Modulus of elasticity: 7.700 N/mm^2

Density: 580kg/m^3 12% MC

Dimensional changes: medium

Hardness: medium

Texture: medium

Porosity: medium.

