

MOHAGANY CROTCH VENEER

Latin names: Entandrophragma cylindricum Sprague.

Commercial Names: (I) Mogano Sapeli , (F) Sapeli , (D) Sapeli Mahagoni

Original names: Scented Mahogany, Aboudikro , Lotue

Mechanical properties: average resistance to longitudinal compression: 60N/mm²

Bending strength: 140N/mm²

Modulus of elasticity: 11.500N/mm²

Density: 690kg/m³ 12%MC

Dimensional changes: small to medium

Hardness: medium

Texture: medium

Porosity: quite high.



DANUBE

No.1 building material company