

RECON VENEER

Latin names: Woods for furniture is usually to eliminate the color differences which arise from log to log and also for aesthetic reasons.

It is therefore the standard practice to vanish the product, whether for technical or , not least , aesthetic reasons.

For example: in the case of walnut – yellow, red or brown in varying intensity

Mechanical properties: Average resistance to longitudinal compression: 65N/mm^2

Bending strength: 135N/mm^2

Modulus of elasticity: 12.000N/mm^2

Density: 930kg/m^3 12%MC

Dimensional changes: small

Hardness: medium to good

Texture: coarse

Porosity: quite high



DANUBE

No.1 building material company