

RED CEDAR QUARTER CUT VENEER

Latin names: Cedrus

Commercial Names: (I) Cedro (F) Cedre,(D) Zeder,(Arabia) Arz, Sharbin

Original names: Cedro, Cedre, Zedar

Mechanical properties: Average resistance to longitudinal compression: 37N/mm^2

Bending strength: 70N/mm^2

Modulus of elasticity: 10.000 N/mm^2

Density: 560kg/m^3 12% MC

Dimensional changes: medium

Hardness: fairly low

Texture: medium

Porosity: medium.



DANUBE

No.1 building material company