

ROSEWOOD VENEER

Latin names: Dalbergia latifolia

Commercial Names: (I)Palissandro (Brazil) , (F) Pallissandro des Indes, (D) ostidisch palisander, (E) palisandro

Original names: Sonokling, Kalaruk , Serisso , Bombay blackwood

Mechanical properties: Average resistance to longitudinal compression: 65 N/mm²

Bending strength: 135N/mm²

Modulus of elasticity: 12.000N/mm²

Density: 850kg/m³ 12%MC

Dimensional changes: medium

Hardness: medium to good

Texture: medium to fine

Porosity: quite high.



DANUBE

No.1 building material company