

SAPELE VENEER

Latin names: Entandrophragma cylindricum Sprague

Commercial Names: (I)Mogano Sapeli, (F) Sapeli , (D) Sapeli Mahogani

Original names: Scented Mahogany, Aboudikro , Lotue

Mechanical properties: Average resistance to longitudinal compression: 60N/mm^2

Bending strength: 140N/mm^2

Modulus of elasticity: 11.500N/mm^2

Density: 690kg/m^3 12%MC

Dimensional changes: small to medium

Hardness: medium

Texture: medium

Porosity: quite high.



DANUBE

No.1 building material company