

SYCAMORE VENEER

- Latin names:** Various species belong to the botanical genus acer among these the following are important in Italy: Acer campestre L., A. pseudoplatanus L., A. opalus mill and A. platanoides.
- Commercial Names:** (I) Acero, (F) Erable,(D) Ahorn, (E) Acre, Sicomoro, (USA) European Maple
- Original names:** Oppio, Rompich, Aierela, Testuccio
- Mechanical properties:** Average resistance to longitudinal compression: 45N/mm^2
Bending strength: 110N/mm^2
Modulus of elasticity: 9.400 N/mm^2
Density: 660kg/m^3 12%MC
Dimensional changes: medium
Hardness: good
Texture: fine
Porosity: low.

