

TECHNICAL DATA REPORT
TEAK VENEER PLYWOOD
1220X2440X3MM

Properties	Unit	Value
Size Tolerance (within panel)	mm	+/-2mm max in length and width
Squareness	mm	+/-2mm
Density	Kg/m ³	770-800
Density Profile @ core	%	85
Internal Bond	N/mm ²	0.65
Modules of Rupture	N/mm ²	30
Modules of Elasticity	N/mm ²	n/a
Surface Soundness	N	2600
Screw Holding		
∅ Face	N	n/a
∅ Edge	N	n/a
Thickness Swelling (24hr)	%	35
Water Absorption (24hr)	%	60
Dimensional Stability (rh35-85%)		
∅ Length/Width		
∅ Thickness	%	0.5
	%	6

(ACCORDING TO EUROPEAN STANDARD EN622-5:1997)

