

## WALNUT BURL VENEER

**Latin names:** Juglans nigra L.

**Commercial Names:** (I) Noce, (F) Noyer, (D) gemeiner walnussbaum, (E) Nogal

**Original names:** Nus , Nogher , Cocolar , Nociara

**Mechanical properties:** Average resistance to longitudinal compression: 60 N/mm<sup>2</sup>

Bending strength: 100N/mm<sup>2</sup>

Modulus of elasticity: 10.800N/mm<sup>2</sup>

Density: 720kg/m<sup>3</sup> 12%MC

Dimensional changes: medium

Hardness: medium

Texture: medium

Porosity: medium



# DANUBE

No.1 building material company