



## **BUILDING MATERIALS FZCO**

### **THE NAME GUARANTEES**

P.O.Box 18022, Jebel Ali Free Zone, DUBAI - U.A.E.

Tel: +971-4-8871234 Fax: +971-4-8871235

Email: [info@aldanube.com](mailto:info@aldanube.com) / [fayaz@aldanube.com](mailto:fayaz@aldanube.com)

## **WENGE VENEER**

**Latin Name:** Millettia Laurenti De Wild, M.

**Commercial Names:** (I) Wenge

**Original Names:** Awong, Anong, Makonge, Kiboto

**Mechanical Properties:** Average resistance to longitudinal compression:  $65\text{N/mm}^2$   
Bending strength:  $150\text{ N/mm}^2$   
Modulus Of Elasticity:  $11.500\text{ N/mm}^2$   
Density:  $780\text{ kg/m}^3$  12% MC  
Dimensional Changes: Medium  
Hardness: Fairly Low  
Texture: Medium to Coarse  
Porosity: Quite High

