

DANUBE
No.1 building material company

BUILDING MATERIALS FZCO **THE NAME GUARANTEES**

P.O.Box 18022, Jebel Ali Free Zone, DUBAI - U.A.E.

Tel: +971-4-8871234 Fax: +971-4-8871235

Email: info@aldanube.com / fayaz@aldanube.com

WHITE OAK VENEER

Country of Origin:	America
Latin Name:	Although the woods marked under the commercial name Oak are produced From three different botanical species, Quercus Petrea Liebel, (or Durmast Oak), Q. Pedunculata Ehrh. (Or Pedunculate Oak) and Q. Pubescens Wild (Or Chene Pubescent), they are hardly distinguishable from one another.
Commercial Names:	(I) Rovere, (F) Rouvre, Chene Peduncule (D) Stieleiche, Traubeneiche, (E) Roble
Original Names:	Roul, Galera, Gettina, Ischia
Mechanical Properties:	Average resistance to longitudinal compression: 60N/mm ² Bending strength: 110 N/mm ² Modulus Of Elasticity: 12.500 N/mm ² Density: 780 kg/m ³ 12% MC Dimensional Changes: Medium to large Hardness: Very Good Texture: Medium Porosity: High Thickness: 0.6 mm

